

## SPECIFICATION OF BITUMEN I5/25

<b>ITEM</b>	<b>Specification</b>	<b>Test Method</b>
Specific gravity @ 25/25 cg	1.01/1.06	D-70
Penetration @ 25 c	25/15	D-5
Softening point c	60/76	D-36
Ductility @25 c	100 min	D-113
Loss on heating(wt) %	0.2 Max	D-6
Drop in penetration after heating %	20 Max	D-6 D-5
Flash point c	250 min	D-92
Solubility in CS <sub>2</sub> (wt) %	99.5 Max	D-4
Spot test	negative	A.A.S.H.O.T102