

Specification of the Bitumen AH-50

Bitumen Grade AH	AH-50
Penetration (25°C, 100g, 5s (0.1mm))	40-60
Ductility (5cm/rain, 15°C)不小于 (cm)	100
Softening point (vc)	45~55
Flash point (COC) (°C)	230
Wax content (%)	3
Density (15°C)(g/ca)	Actual measurement records
Solubility trichlorethylene (%)	99.0
Film heating (163°C, 5h)	0.8
Pen ratio(%)	58
Ductility (25°C) is not less than	40
Ductility (15°C)(cm)	Actual measurement records