

Cutback Bitumen MC-250 Specification Data Sheet

Property	Test Method (ASTM / EN)	Min	Max
Kinematic Viscosity @ 60°C	ASTM D2170	250 cSt	500 cSt
Flash Point (Tag Open Cup)	ASTM D1310	66°C	—
Distillate, Volume % to 225°C	ASTM D402	—	10%
Distillate, Volume % to 260°C	ASTM D402	15%	55%
Distillate, Volume % to 316°C	ASTM D402	60%	87%
Residue from Distillation to 360°C (by volume)	ASTM D402	67%	—
Penetration @ 25°C, 100g, 5s	ASTM D5	30 dmm	120 dmm
Ductility @ 25°C	ASTM D113	120 cm	—
Solubility in Trichloroethylene	ASTM D2042	99%	—
Water Content (by volume)	ASTM D95	—	0.2%