

Cutback Bitumen MC-800 Specification Data Sheet

Property	Test Method (ASTM / EN)	Min	Max
Kinematic Viscosity @ 60°C	ASTM D2170	800 cSt	1600 cSt
Flash Point (Tag Open Cup)	ASTM D1310	66°C	—
Distillation to 360°C, % Volume	ASTM D402	—	40
Penetration @ 25°C, 100g, 5s	ASTM D5	120 dmm	250 dmm
Ductility @ 25°C, 5cm/min	ASTM D113	100 cm	—
Solubility in Trichloroethylene	ASTM D2042	99%	—
Water Content (by Volume)	ASTM D95	—	0.2%