

## SPECIFICATION of PMB AE1

| Property                     | Unit | Test Method | Requirement (A-E2) |
|------------------------------|------|-------------|--------------------|
| Softening Point              | °C   | MB-17       | 65 – 85            |
| Elastic Recovery @ 15 °C     | %    | MB-4        | > 60               |
| Dynamic Viscosity @ 165 °C   | Pa·s | MB-18       | ≤ 0.60             |
| Storage Stability @ 180 °C   | °C   | MB-6        | ≤ 5                |
| Flash Point                  | °C   | ASTM D92    | ≥ 230              |
| Mass Change (RTFOT)          | %    | MB-3        | ≤ 1.0              |
| Softening Point after RTFOT  | °C   | MB-17       | 63 min             |
| Elastic Recovery after RTFOT | %    | MB-4        | > 50               |